

Braskem H 201 Fiber Extrusion Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Extrusion Grade

Material Notes:

Applications: Staple fibers for carpets and blankets; continuous filament for ropes, cords and rugs. Information provided by Braskem

Order this product through the following link:

http://www.lookpolymers.com/polymer_Braskem-H-201-Fiber-Extrusion-Polypropylene.php

Physical Properties	Metric	English	Comments
Density	0.905 g/cc	0.0327 lb/in ³	ASTM D792A
Melt Flow	20 g/10 min @Load 2.16 kg, Temperature 230 °C	20 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238L

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	94	94	ASTM D785
Tensile Strength, Yield	35.0 MPa	5080 psi	ASTM D638
Elongation at Yield	11 %	11 %	ASTM D638
Flexural Modulus	1.58 GPa	229 ksi	ASTM D790
Izod Impact, Notched	0.260 J/cm @Temperature 23.0 °C	0.487 ft-lb/in @Temperature 73.4 °F	ASTM D256A

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	97.0 °C	207 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	57.0 °C	135 °F	ASTM D648
Vicat Softening Point	153 °C	307 °F	-1kg; ASTM D1525

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China