

Braskem TR3350C Random Copolymer Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene Copolymer

Material Notes:

Description: High melt flow, excellent see-through clarity, superior color and processing stability, low odor. Applications: Suggested uses include reusable food containers, housewares, fast-cycle injection molding. Process: Injection Molding This resin meets the requirements for olefin polymers as defined in 21 CFR, section 177.1520 issued by FDA – Food and Drugs Administration. The additives present are covered in appropriate regulation by FDA. Information provided by Braskem

Order this product through the following link:

http://www.lookpolymers.com/polymer_Braskem-TR3350C-Random-Copolymer-Polypropylene.php

Physical Properties	Metric	English	Comments
Melt Flow	35 g/10 min @Load 2.16 kg, Temperature 230 °C	35 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength	31.0 MPa	4500 psi	2 in/min; ASTM D638
Elongation at Yield	9.0 %	9.0 %	2 in/min; ASTM D638
Flexural Modulus	1.17 GPa	170 ksi	0.05 in/min, 1% secant; ASTM D-790A
Izod Impact, Notched	0.481 J/cm	0.900 ft-lb/in	ASTM D256A

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China