

Bulk Molding Compounds BMC A50-XHS Bulk molding compound

Category : Polymer , Thermoset , Polyester, TS

Material Notes:

Description: BMC A50XHS is a high strength bulk molding compound. It can be supplied in bulk or extruded in preweighted slugs. Due to the excellent flow and controlled reactivity, BMC A50XHS is well suited for injection, transfer or compression molding. Typical applications are circuit breakers, lighting housings and structural parts. Information provided by Bulk Molding Compounds

Order this product through the following link:

http://www.lookpolymers.com/polymer_Bulk-Molding-Compounds-BMC-A50-XHS-Bulk-molding-compound.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.79 - 1.99 g/cc	1.79 - 1.99 g/cc	molded
Linear Mold Shrinkage	0.0015 - 0.0025 cm/cm	0.0015 - 0.0025 in/in	

Mechanical Properties	Metric	English	Comments
Hardness, Barcol	30 - 40	30 - 40	
Tensile Strength at Break	57.2 - 71.0 MPa	8300 - 10300 psi	
Flexural Yield Strength	124 - 152 MPa	18000 - 22000 psi	
Flexural Modulus	11.7 - 13.1 GPa	1700 - 1900 ksi	
Compressive Strength	116 - 143 MPa	16800 - 20800 psi	
Izod Impact, Notched	5.34 - 6.41 J/cm	10.0 - 12.0 ft-lb/in	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	>= 260 °C	>= 500 °F	
Flammability, UL94	V-0	V-0	

Electrical Properties	Metric	English	Comments
Dielectric Strength	14.8 - 16.7 kV/mm	375 - 425 kV/in	Short Time
Arc Resistance	>= 186 sec	>= 186 sec	
Comparative Tracking Index	<= 500 V	<= 500 V	

Processing Properties	Metric	English	Comments
Mold Temperature	138 - 166 °C	280 - 330 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China