

Bulk Molding Compounds BMC T10(GP) General Purpose Molding Compound

Category : Polymer , Thermoset , Polyester , TS , Polyester (Thermoset) - Rigid

Material Notes:

BMC T10(GP) is a general purpose molding compound. Due to the excellent flow and controlled reactivity, BMC T10(GP) is well suited for injection, transfer or compression molding of intricate parts. Typical applications are circuit breakers, insulators, bobbins and electrical connectors. Information provided by Bulk Molding Compounds, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Bulk-Molding-Compounds-BMC-T10GP-General-Purpose-Molding-Compound.php

Physical Properties	Metric	English	Comments
Density	1.92 - 2.12 g/cc	0.0694 - 0.0766 lb/in ³	Molded
Linear Mold Shrinkage	0.0025 - 0.035 cm/cm	0.0025 - 0.035 in/in	

Mechanical Properties	Metric	English	Comments
Hardness, Barcol	30 - 40	30 - 40	
Tensile Strength	27.6 - 41.4 MPa	4000 - 6000 psi	
Flexural Strength	79.3 - 107 MPa	11500 - 15500 psi	
Flexural Modulus	11.7 - 13.1 GPa	1700 - 1900 ksi	
Compressive Strength	110 - 138 MPa	16000 - 20000 psi	
Izod Impact, Notched	2.67 - 3.74 J/cm	5.00 - 7.00 ft-lb/in	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	>= 260 °C	>= 500 °F	
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
Dielectric Strength	14.2 - 16.1 kV/mm	360 - 410 kV/in	short time
Arc Resistance	>= 183 sec	>= 183 sec	
Comparative Tracking Index	>= 500 V	>= 500 V	

Processing Properties	Metric	English	Comments
Processing Temperature	138 - 166 °C	280 - 330 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China