

Bulk Molding Compounds tetra-DUR N 4111 Bulk Molding Compound

Category : Polymer , Thermoset , Polyester , TS , Polyester (Thermoset) - Rigid

Material Notes:

Smooth, high gloss surface. Low profile. Typical Applications - Requiring mechanical strength, abrasion resistance, dimensional stability, electrical insulation, electrostatic dissipation (explosion protection), thermal stability, color retention, chemical stability, zero shrink/class-A-surface, and uniform color. Information provided by Bulk Molding Compounds, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Bulk-Molding-Compounds-tetra-DUR-N-4111-Bulk-Molding-Compound.php

Physical Properties	Metric	English	Comments
Density	1.90 - 2.00 g/cc	0.0686 - 0.0723 lb/in ³	ISO 1138
Linear Mold Shrinkage	-0.00100 - 0.0010 cm/cm	-0.00100 - 0.0010 in/in	processing, expansion/shrinkage; ISO 2577

Mechanical Properties	Metric	English	Comments
Tensile Strength	30.0 - 35.0 MPa	4350 - 5080 psi	ISO 527
Flexural Strength	90.0 - 110 MPa	13100 - 16000 psi	ISO 178
Flexural Modulus	9.00 - 12.0 GPa	1310 - 1740 ksi	ISO 178
Compressive Strength	160 - 180 MPa	23200 - 26100 psi	ISO 604
Charpy Impact Unnotched	>= 1.50 J/cm ²	>= 7.14 ft-lb/in ²	ISO 179
Charpy Impact, Notched	>= 1.50 J/cm ²	>= 7.14 ft-lb/in ²	ISO 179

Thermal Properties	Metric	English	Comments
CTE, linear	15.0 - 22.0 µm/m-°C	8.33 - 12.2 µin/in-°F	VDE 0304 T1
Deflection Temperature at 1.8 MPa (264 psi)	>= 240 °C	>= 464 °F	ISO 75
Flammability, UL94	HB	HB	
Shrinkage	<= 0.00 %	<= 0.00 %	post molding; ISO 2577

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+14 ohm-cm	1.00e+14 ohm-cm	IEC 60093
Surface Resistance	1.00e+13 ohm	1.00e+13 ohm	IEC 60093
Dielectric Constant	4.5 @Frequency 100 Hz	4.5 @Frequency 100 Hz	IEC 60250

Electrical Properties	Metric 20.0 kV/mm	English 500 kV/in	Comments
Dielectric Strength	@Thickness 1.00 mm	@Thickness 0.0394 in	IEC 60243
Dielectric Loss Index	<= 0.030 @Frequency 100 Hz	<= 0.030 @Frequency 100 Hz	IEC 60250
Comparative Tracking Index	>= 600 V	>= 600 V	IEC 60112

Descriptive Properties	Value	Comments
Water Absorption	<30 mg/1d	ISO 62

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China