

CEN® Electronic Material CN Polyimide Film, 3 Mil Thickness

Category: Polymer, Thermoset, Polyimide, TS, Polyimide, Thermoset Film

Material Notes:

CEN®CN polyimide film is typical general-purpose polyimide film and has been used successfully in applications at temperatures as low as -269°C (-452°F) and as high as 400°C (752°F). CN film can be laminated, metallized, punched, formed or adhesive coated. CEN®CN is used for applications that require an all-polyimide film with an excellent balance of properties over a wide range of temperatures. Applications: mechanical parts, electronic parts, electrical insulation, pressure sensitive tape, fiber optics cable, insulation blankets, insulation tubing, automotive diaphragms sensors and manifolds. All information provided by CEN Electronic Material Co., LTD.

Order this product through the following link:

http://www.lookpolymers.com/polymer_CEN-Electronic-Material-CN-Polyimide-Film-3-Mil-Thickness.php

Physical Properties	Metric	English	Comments
Thickness	70.0 - 80.0 microns	2.76 - 3.15 mil	

Mechanical Properties	Metric	English	Comments
Film Tensile Strength at Yield, MD	140 MPa	20300 psi	
Film Tensile Strength at Yield, TD	130 MPa	18900 psi	
Film Elongation at Yield, MD	>= 45 %	>= 45 %	
Film Elongation at Yield, TD	>= 45 %	>= 45 %	

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 5.00e+13 ohm-cm	>= 5.00e+13 ohm-cm	
Surface Resistance	>= 5.00e+14 ohm	>= 5.00e+14 ohm	
Dielectric Strength	>= 160 kV/mm	>= 4060 kV/in	

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China