

## CEN® Electronic Material CV Polyimide Film, 4 Mil Thickness

Category : Polymer , Thermoset , Polyimide, TS , Polyimide, Thermoset Film

### Material Notes:

CEN®CV polyimide film keeps the same film properties as CEN®CN polyimide film, and has an excellent balance of physical, chemical, and electrical properties over a wide temperature range. With superior dimensional stability at elevated temperatures, CEN®CV polyimide film is ideal for high temperature applications that require a low-shrinkage film. Applications: sensors, gaskets, electronic parts, pin grids, coverlay film, TAB tapes, reinforced board for FPC. All information provided by CEN Electronic Material Co., LTD.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_CEN-Electronic-Material-CV-Polyimide-Film-4-Mil-Thickness.php](http://www.lookpolymers.com/polymer_CEN-Electronic-Material-CV-Polyimide-Film-4-Mil-Thickness.php)

Physical Properties	Metric	English	Comments
Thickness	94.0 - 106 microns	3.70 - 4.17 mil	ASTM D374

Mechanical Properties	Metric	English	Comments
Film Tensile Strength at Yield, MD	150 MPa	21800 psi	ASTM D882
Film Tensile Strength at Yield, TD	140 MPa	20300 psi	ASTM D882
Film Elongation at Yield, MD	>= 45 %	>= 45 %	ASTM D882
Film Elongation at Yield, TD	>= 50 %	>= 50 %	ASTM D882

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 1.00e+13 ohm-cm	>= 1.00e+13 ohm-cm	ASTM D257
Surface Resistance	>= 1.00e+14 ohm	>= 1.00e+14 ohm	ASTM D257
Dielectric Strength	>= 140 kV/mm	>= 3560 kV/in	ASTM D149

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China