

CEN® Electronic Material CV Polyimide Film, 6 Mil Thickness

Category: Polymer, Thermoset, Polyimide, TS, Polyimide, Thermoset Film

Material Notes:

CEN®CV polyimide film keeps the same film properties as CEN®CN polyimide film, and has an excellent balance of physical, chemical, and electrical properties over a wide temperature range. With superior dimensional stability at elevated temperatures, CEN®CV polyimide film is ideal for high temperature applications that require a low-shrinkage film. Applications: sensors, gaskets, electronic parts, pin grids, coverlay film, TAB tapes, reinforced board for FPCAll information provided by CEN Electronic Material Co., LTD.

Order this product through the following link:

http://www.lookpolymers.com/polymer_CEN-Electronic-Material-CV-Polyimide-Film-6-Mil-Thickness.php

Physical Properties	Metric	English	Comments
Thickness	140 - 160 microns	5.51 - 6.30 mil	ASTM D374

Mechanical Properties	Metric	English	Comments
Film Tensile Strength at Yield, MD	140 MPa	20300 psi	ASTM D882
Film Tensile Strength at Yield, TD	130 MPa	18900 psi	ASTM D882
Film Elongation at Yield, MD	>= 40 %	>= 40 %	ASTM D882
Film Elongation at Yield, TD	>= 45 %	>= 45 %	ASTM D882

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 5.00e+12 ohm-cm	>= 5.00e+12 ohm-cm	ASTM D257
Surface Resistance	>= 5.00e+13 ohm	>= 5.00e+13 ohm	ASTM D257
Dielectric Strength	>= 120 kV/mm	>= 3050 kV/in	ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China