

CLAL-MSX ARCAP Anticorrosion AP4 H13 3/4 hard, Drawn Copper Alloy

Category : Metal , Nonferrous Metal , Copper Alloy , Nickel Alloy

Material Notes:

Description: The AP4 grade is less easy to turn than the other grades of ARCAP. It can however be machined without more difficulty than the nickel chromium molybdenum steels. **High Corrosion Resistance:** ARCAP alloys are very corrosion resistant to the majority of chemical and physical environments. CLAL can provide data for the corrosion resistance of ARCAP alloys. In particular ARCAP alloys have a very high resistance to scaling and clogging of pipes by hard water and the blocking of pipes used for transport powder products such as sodium aluminate, cement, etc. **High Mechanical Properties:** In annealed temper ARCAP, alloys have an elongation up to 45 %, which allows deep drawing. In spring temper the ultimate tensile strength is above 800 MPa. **Non-Magnetic:** A detector sensitive to 1/10 of nanotesla, placed at less than 1 mm from ARCAP alloys will not show any magnetic interference. This non magnetism is kept even at very low temperatures (measured at 4.2° k). **Stable Resistivity:** Temperature variations have almost no effect on the resistivity of ARCAP alloys. The temperature coefficient of the grade AP4 is $4 \times 10^{-5}/^{\circ}\text{C}$ and $25 \times 10^{-5}/^{\circ}\text{C}$ for the other grades. **Excellent Behaviour At Low Temperature:** At low temperatures the mechanical properties of ARCAP alloys are improved. A cryogenic application shows that the ultimate tensile strength and the yield strength increase without any diminution of the elongation or the impact strength. **Very Easy To Process:** ARCAP alloys are easily processed whether by forging, stamping, deep drawing, machining, welding or brazing. They are also easily plated. Information provided by CLAL-MSX

Order this product through the following link:

http://www.lookpolymers.com/polymer_CLAL-MSX-ARCAP-Anticorrosion-AP4-H13-34-hard-Drawn-Copper-Alloy.php

Physical Properties	Metric	English	Comments
Density	8.91 g/cc	0.322 lb/in ³	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	600 - 650 MPa	87000 - 94300 psi	Rod
Elongation at Break	>= 2.0 %	>= 2.0 %	L ₀ =50 mm
Modulus of Elasticity	145 GPa	21000 ksi	

Thermal Properties	Metric	English	Comments
CTE, linear	16.0 $\mu\text{m}/\text{m}\cdot^{\circ}\text{C}$	8.89 $\mu\text{in}/\text{in}\cdot^{\circ}\text{F}$	
	@Temperature 0.000 - 300 °C	@Temperature 32.0 - 572 °F	
Thermal Conductivity	17.0 $\mu\text{m}/\text{m}\cdot^{\circ}\text{C}$	9.44 $\mu\text{in}/\text{in}\cdot^{\circ}\text{F}$	
	@Temperature 0.000 - 600 °C	@Temperature 32.0 - 1110 °F	
Thermal Conductivity	22.5 W/m-K	156 BTU-in/hr-ft ² -°F	
	@Temperature <=20.0 °C	@Temperature <=68.0 °F	

Thermal Properties	Metric ^{J/m²-K}	English ^{J-in/hr-ft²-°F}	Comments
	@Temperature <=200 °C	@Temperature <=392 °F	
Melting Point	1225 - 1285 °C	2237 - 2345 °F	
Solidus	1225 °C	2237 °F	
Liquidus	1285 °C	2345 °F	

Optical Properties	Metric	English	Comments
Reflection Coefficient, Visible (0-1)	0.700	0.700	Relative to Silver = 1

Component Elements Properties	Metric	English	Comments
Copper, Cu	53.5 %	53.5 %	
Nickel, Ni	45 %	45 %	
Other	2.0 %	2.0 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.0000490 ohm-cm	0.0000490 ohm-cm	

Descriptive Properties	Value	Comments
Color	White	
Non Magnetism request	1E-05	OERSTED
Temperature Coefficient	4E-05	K-1

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China