

CLAL-MSX NICLAL 1300 H14 4/4 Hard Copper Alloy, Free Cutting Nickel-Silver

Category : Metal , Nonferrous Metal , Copper Alloy

Material Notes:

Main Characteristics: Good ductility Good corrosion resistance Typical Applications: High volume turned parts Keys Information provided by CLAL-MSX

Order this product through the following link:

http://www.lookpolymers.com/polymer_CLAL-MSX-NICLAL-1300-H14-44-Hard-Copper-Alloy-Free-Cutting-Nickel-Silver.php

Physical Properties	Metric	English	Comments
Density	8.65 g/cc	0.313 lb/in ³	

Mechanical Properties	Metric	English	Comments
Hardness, Vickers	>= 175	>= 175	
Tensile Strength, Ultimate	570 - 780 MPa	82700 - 113000 psi	
Tensile Strength, Yield	>= 55.0 MPa @Strain 0.200 %	>= 7980 psi @Strain 0.200 %	
Elongation at Break	3.0 %	3.0 %	100 A
Modulus of Elasticity	130 GPa	18900 ksi	

Thermal Properties	Metric	English	Comments
CTE, linear	16.0 $\mu\text{m}/\text{m}\cdot\text{°C}$ @Temperature 0.000 - 100 °C	8.89 $\mu\text{in}/\text{in}\cdot\text{°F}$ @Temperature 32.0 - 212 °F	
Specific Heat Capacity	0.410 J/g- °C	0.0980 BTU/lb- °F	
Thermal Conductivity	33.0 W/m-K	229 BTU-in/hr-ft ² - °F	
Melting Point	1020 °C	1870 °F	

Component Elements Properties	Metric	English	Comments
Copper, Cu	63 %	63 %	
Lead, Pb	<= 1.0 %	<= 1.0 %	
Nickel, Ni	13 %	13 %	
Zinc, Zn	<= 23 %	<= 23 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.0000230 ohm-cm	0.0000230 ohm-cm	

Descriptive Properties	Value	Comments
Color	Ivory	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China