

## COI Ceramics Nicalon™ HRV SiCO Ceramic Fiber

Category : Ceramic , Carbide

### Material Notes:

**Description:** The fiber is homogeneously composed of ultra-fine beta-SiC crystallites and an amorphous mixture of silicon, carbon, and oxygen. The fiber has excellent strength and modulus properties for ceramic fibers, and retains its properties at high temperatures.

**Nicalon™** is highly resistant to oxidation and chemical attack. **Product Forms:** Continuous Fiber: Supplied as multi-filament tow, spooled on 3 inch ID bobbins to 500 meters in length (100 grams in weight). Also available in random lengths at a reduced price. Woven Cloth: Available in three weave styles as shown in Table 2. Woven cloth is typically supplied as 1-meter-wide continuous rolls of specific lengths. Other weave or braid styles can be made available. Chopped Fiber: Available of 1-mm length chopped multi-filament tow. Longer lengths also available. Packaged as 3 kg containers. Felt / Mat: Random lengths of Nicalon™ ceramic fiber in a PVA binder. Customizable areal weights, shapes and sizes. **Uses:** Nicalon™ ceramic fiber can be used as a reinforcement for plastic, ceramic, and metal matrix composites to produce high performance composite materials. Surface treatments are normally recommended to facilitate processing and maximize composite properties Nicalon™ can also be used to form fibrous products such as high temperature insulation, filters, etc. Its resistance to chemical attack allows it to be used in harsh environments. A low dielectric (high volume resistivity) fiber that is designed to offer an optimum balance of mechanical and electrical properties in dielectric structures. Information from COI Ceramics, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_COI-Ceramics-Nicalon-HRV-SiCO-Ceramic-Fiber.php](http://www.lookpolymers.com/polymer_COI-Ceramics-Nicalon-HRV-SiCO-Ceramic-Fiber.php)

Physical Properties	Metric	English	Comments
Density	2.32 g/cc	0.0838 lb/in <sup>3</sup>	
Filament Diameter	14 μm	14 μm	
Fiber Count	2000 dtex	1800 denier	

Mechanical Properties	Metric	English	Comments
Tensile Strength	2800 MPa	406000 psi	
Tensile Modulus	180 GPa	26100 ksi	

Thermal Properties	Metric	English	Comments
CTE, linear	3.90 μm/m-°C @Temperature 900 °C	2.17 μin/in-°F @Temperature 1650 °F	

Component Elements Properties	Metric	English	Comments
Carbon, C	32 %	32 %	
Oxygen, O	12 %	12 %	
Silicon, Si	57 %	57 %	

Electrical Properties	Metric	English	Comments
Volume Resistivity	$\geq 1.00e+6$ ohm-cm	$\geq 1.00e+6$ ohm-cm	
Dielectric Constant	6.4	6.4	
Dissipation Factor	0.050	0.050	

Descriptive Properties	Value	Comments
Filaments per tow	500	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China