

## C.O.I.M. EXTER S® S 105 Orthophthalic Resin

Category : Polymer , Thermoset , Polyester, TS , Polyester (Thermoset) - Rigid

### Material Notes:

Description: The Exter S product line contains a large number of unsaturated polyester resin products with an array of properties and applications. Specific Notes for EXTER S® S 105: Medium reactivity resin suitable for synthetic marble. Information provided by P.A.T. Products, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_COIM-EXTER-S-S-105-Orthophthalic-Resin.php](http://www.lookpolymers.com/polymer_COIM-EXTER-S-S-105-Orthophthalic-Resin.php)

Physical Properties	Metric	English	Comments
Brookfield Viscosity	550 - 750 cP @Temperature 25.0 °C	550 - 750 cP @Temperature 77.0 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	63.0 - 65.0 °C	145 - 149 °F	

Chemical Properties	Metric	English	Comments
Styrene Content	34 - 36 %	34 - 36 %	

Descriptive Properties	Value	Comments
Rigidity	medium/low	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China