

C.O.I.M. EXTER S® S 203 Special Laminate

Category : Polymer , Thermoset , Polyester, TS , Polyester (Thermoset) - Rigid

Material Notes:

Description: The Exter S product line contains a large number of unsaturated polyester resin products with an array of properties and applications. Specific Notes for EXTER S® S 203: Polyester resin TMPDE based for varnishes Information provided by P.A.T. Products, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_COIM-EXTER-S-S-203-Special-Laminate.php

Physical Properties	Metric	English	Comments
Brookfield Viscosity	1000 - 1400 cP @Temperature 25.0 °C	1000 - 1400 cP @Temperature 77.0 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	80.0 °C	176 °F	

Chemical Properties	Metric	English	Comments
Styrene Content	24 - 26 %	24 - 26 %	

Descriptive Properties	Value	Comments
Rigidity	medium	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China