

C.O.I.M. LARIPUR® LPR6325 Special Adipate Ester Polyurethane

Category : Polymer , Thermoplastic , Elastomer, TPE , Polyester, TP , Polyester Thermoplastic Elastomer , Polyurethane, TP

Material Notes:

Description: The products of the LARIPUR® line are thermoplastic polyurethanes. These products combine the technology of thermoplastic products with the features of polyurethanes:Excellent abrasion resistanceGreat flexibility with constancy at temperature variationsGood compression resistanceGood water and light resistanceGood resistance to oils, fats and to many types of solventsSeries 25 Special Adipate Ester: These products are based on saturated polyesters. Products are based on saturated polyester. The features are similar to those of Series 20 but, by comparison, they are characterized by a higher resistance to hydrolysis and improved flexibility at low temperatures.

Information provided by P.A.T. Products, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_COIM-LARIPUR-LPR6325-Special-Adipate-Ester-Polyurethane.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.24 g/cc	1.24 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	62	62	ASTM D2240
Tensile Strength, Yield	70.2 MPa	10200 psi	ASTM D412
Elongation at Break	370 %	370 %	ASTM D412
50% Modulus	0.0212 GPa	3.07 ksi	ASTM D412
100% Modulus	0.0241 GPa	3.50 ksi	ASTM D412
300% Modulus	0.0511 GPa	7.41 ksi	ASTM D412
Flexural Modulus	0.350 GPa	50.8 ksi	ASTM D790
Izod Impact, Notched (ISO)	4.70 kJ/m ² @Temperature -20.0 °C	2.24 ft-lb/in ² @Temperature -4.00 °F	ASTM D256
Tear Strength	193 kN/m	1100 pli	ASTM D624
Abrasion	40	40	mm ³ , Abrasion Loss; DIN 53516
Torsional Stiffness	80.0 MPa	11600 psi	+20°C; ASTM D1043
	460 MPa	66700 psi	-20°C; ASTM D1043

Thermal Properties	Metric	English	Comments
Vicat Softening Point	156 °C	313 °F	ASTM D1525

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China