

CP-Polymer-Technik Wellamid® 6000 GS 30 HWUVCP 30% Glass Sphere Filled Nylon 6, UV Stabilized, Heat Stabilized, Dry

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, Glass Bead Filled

Material Notes:

Information provided by CP-Polymer-Technik GmbH & Co. KG

Order this product through the following link:

http://www.lookpolymers.com/polymer_CP-Polymer-Technik-Wellamid-6000-GS-30-HWUVCP-30-Glass-Sphere-Filled-Nylon-6-UV-Stabilized-Heat-Stabilized-Dry.php

Physical Properties	Metric	English	Comments
Density	1.35 g/cc	0.0488 lb/in ³	ISO 1183
Moisture Absorption at Equilibrium	1.8 - 2.3 %	1.8 - 2.3 %	23°C/50%RH; DIN 53495
Linear Mold Shrinkage	0.0080 - 0.010 cm/cm @Thickness 4.00 mm	0.0080 - 0.010 in/in @Thickness 0.157 in	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	80.0 MPa	11600 psi	5 mm/min; ISO 527
Elongation at Break	8.5 %	8.5 %	5 mm/min; ISO 527
Tensile Modulus	4.50 GPa	653 ksi	ISO 527
Flexural Modulus	4.00 GPa	580 ksi	DIN 52457
Charpy Impact Unnotched	3.00 J/cm ² @Temperature 23.0 °C	14.3 ft-lb/in ² @Temperature 73.4 °F	ISO 179
Charpy Impact, Notched	0.600 J/cm ² @Temperature 23.0 °C	2.86 ft-lb/in ² @Temperature 73.4 °F	ISO 179

Thermal Properties	Metric	English	Comments
CTE, linear	50.0 μm/m-°C @Temperature 23.0 - 80.0 °C	27.8 μin/in-°F @Temperature 73.4 - 176 °F	DIN 53752
Melting Point	215 °C	419 °F	Kofler
Deflection Temperature at 0.46 MPa (66 psi)	190 °C	374 °F	ISO 179
Deflection Temperature at 1.8 MPa (264 psi)	80.0 °C	176 °F	ISO 179
Vicat Softening Point	200 °C	392 °F	50 N; ISO 306

Thermal Properties	Metric	English	Comments
Flammability, UL94	@Thickness 1.60 mm	@Thickness 0.0630 in	Stufe; IEC 707
	HB	HB	Stufe; IEC 707
	@Thickness 3.20 mm	@Thickness 0.126 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 93
Surface Resistance	1.00e+12 ohm	1.00e+12 ohm	ISO 3915
Dielectric Constant	4.0	4.0	IEC 250
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dielectric Strength	35.0 kV/mm	889 kV/in	IEC 243-1
Dielectric Loss Index	0.020	0.020	At 1 MHz; IEC 250
Comparative Tracking Index	450 V	450 V	Stufe; IEC 112

Processing Properties	Metric	English	Comments
Melt Temperature	250 - 270 °C	482 - 518 °F	
Mold Temperature	60.0 - 90.0 °C	140 - 194 °F	

Descriptive Properties	Value	Comments
Back Pressure	Low	
Holding Pressure	High	
Injection Speed	Medium	
Screw Speed	High	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China