

## CP-Polymer-Technik Wellamid® 6000 GV 30 HW 30% Glass Fiber Nylon 6, Heat Stabilized, Conditioned

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , 30% Glass Fiber Filled

### Material Notes:

Information provided by CP-Polymer-Technik GmbH & Co. KG

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_CP-Polymer-Technik-Wellamid-6000-GV-30-HW-30-Glass-Fiber-Nylon-6-Heat-Stabilized-Conditioned.php](http://www.lookpolymers.com/polymer_CP-Polymer-Technik-Wellamid-6000-GV-30-HW-30-Glass-Fiber-Nylon-6-Heat-Stabilized-Conditioned.php)

Physical Properties	Metric	English	Comments
Density	1.35 g/cc	0.0488 lb/in <sup>3</sup>	ISO 1183
Moisture Absorption at Equilibrium	1.8 - 2.3 %	1.8 - 2.3 %	23°C/50%RH, Starting when dry; DIN 53495
Linear Mold Shrinkage	0.0020 cm/cm @Thickness 4.00 mm	0.0020 in/in @Thickness 0.157 in	
Linear Mold Shrinkage, Transverse	0.0080 cm/cm @Thickness 4.00 mm	0.0080 in/in @Thickness 0.157 in	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	105 MPa	15200 psi	5 mm/min; ISO 527
Elongation at Break	4.5 %	4.5 %	5 mm/min; ISO 527
Tensile Modulus	6.00 GPa	870 ksi	ISO 527
Charpy Impact Unnotched	10.0 J/cm <sup>2</sup> @Temperature 23.0 °C	47.6 ft-lb/in <sup>2</sup> @Temperature 73.4 °F	ISO 179
Charpy Impact, Notched	2.00 J/cm <sup>2</sup> @Temperature 23.0 °C	9.52 ft-lb/in <sup>2</sup> @Temperature 73.4 °F	ISO 179

Thermal Properties	Metric	English	Comments
Melting Point	215 °C	419 °F	Kofler

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+12 ohm-cm	1.00e+12 ohm-cm	IEC 93
Surface Resistance	1.00e+10 ohm	1.00e+10 ohm	ISO 3915
	7.0	7.0	

Dielectric Constant Electrical Properties	Metric @ Frequency 1e+6 Hz	English @ Frequency 1e+6 Hz	IEC 250 Comments
Dielectric Strength	35.0 kV/mm	889 kV/in	IEC 243-1
Dielectric Loss Index	0.22	0.22	At 1 MHz; IEC 250

Processing Properties	Metric	English	Comments
Melt Temperature	250 - 280 °C	482 - 536 °F	
Mold Temperature	60.0 - 90.0 °C	140 - 194 °F	

Descriptive Properties	Value	Comments
Back Pressure	Low	
Holding Pressure	High	
Injection Speed	Medium to High	
Screw Speed	High	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China