

## CP-Polymer-Technik Wellamid® 6000 HWV0CP Nylon 6, Flame Protection, Heat Stabilized, Conditioned

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , Unreinforced, Flame Retardant

### Material Notes:

Information provided by CP-Polymer-Technik GmbH & Co. KG

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_CP-Polymer-Technik-Wellamid-6000-HWV0CP-Nylon-6-Flame-Protection-Heat-Stabilized-Conditioned.php](http://www.lookpolymers.com/polymer_CP-Polymer-Technik-Wellamid-6000-HWV0CP-Nylon-6-Flame-Protection-Heat-Stabilized-Conditioned.php)

| Physical Properties                | Metric                                     | English                                     | Comments                                 |
|------------------------------------|--|---|--|
| Density                            | 1.15 g/cc                                  | 0.0415 lb/in <sup>3</sup>                   | ISO 1183                                 |
| Moisture Absorption at Equilibrium | 2.5 - 3.3 %                                | 2.5 - 3.3 %                                 | 23°C/50%RH, Starting when dry; DIN 53495 |
| Linear Mold Shrinkage              | 0.0080 - 0.012 cm/cm<br>@Thickness 4.00 mm | 0.0080 - 0.012 in/in<br>@Thickness 0.157 in |  |

| Mechanical Properties   | Metric   | English  | Comments           |
|-------------------------|--|--|--------------------|
| Tensile Strength, Yield | 50.0 MPa                                       | 7250 psi   | 50 mm/min; ISO 527 |
| Elongation at Break     | 30 %   | 30 %   | 50 mm/min; ISO 527 |
| Elongation at Yield     | 12 %   | 12 %   | 50 mm/min; ISO 527 |
| Tensile Modulus         | 1.30 GPa                                       | 189 ksi  | ISO 527            |
| Charpy Impact Unnotched | NB<br>@Temperature 23.0 °C                     | NB<br>@Temperature 73.4 °F                         | ISO 179            |
| Charpy Impact, Notched  | 1.50 J/cm <sup>2</sup><br>@Temperature 23.0 °C | 7.14 ft-lb/in <sup>2</sup><br>@Temperature 73.4 °F | ISO 179            |

| Thermal Properties | Metric | English | Comments |
|--------------------|--------|---------|----------|
| Melting Point      | 215 °C | 419 °F  | Kofler   |

| Electrical Properties | Metric                    | English                   | Comments |
|-----------------------|---------------------------|---------------------------|----------|
| Volume Resistivity    | 1.00e+12 ohm-cm           | 1.00e+12 ohm-cm           | IEC 93   |
| Surface Resistance    | 1.00e+10 ohm              | 1.00e+10 ohm              | ISO 3915 |
| Dielectric Constant   | 6.0<br>@Frequency 1e+6 Hz | 6.0<br>@Frequency 1e+6 Hz | IEC 250  |

| Electrical Properties      | Metric | English | Comments          |
|----------------------------|--------|---------|-------------------|
| Dielectric Loss Index      | 0.25   | 0.25    | At 1 MHz; IEC 250 |
| Comparative Tracking Index | 600 V  | 600 V   | Stufe; IEC 112    |

| Processing Properties | Metric         | English      | Comments |
|-----------------------|----------------|--------------|----------|
| Melt Temperature      | 245 - 265 °C   | 473 - 509 °F |          |
| Mold Temperature      | 50.0 - 90.0 °C | 122 - 194 °F |          |

| Descriptive Properties | Value  | Comments |
|------------------------|--------|----------|
| Back Pressure          | Low    |          |
| Holding Pressure       | High   |          |
| Injection Speed        | Medium |          |
| Screw Speed            | Medium |          |

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China