

CP-Polymer-Technik Wellamid® 6000/50 HWUVCP Nylon 6, Impact Modified Until 0°C, UV Stabilized, Heat Stabilized, Dry

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, Impact Grade

Material Notes:

Information provided by CP-Polymer-Technik GmbH & Co. KG

Order this product through the following link:

http://www.lookpolymers.com/polymer_CP-Polymer-Technik-Wellamid-600050-HWUVCP-Nylon-6-Impact-Modified-Until-0C-UV-Stabilized-Heat-Stabilized-Dry.php

Physical Properties	Metric	English	Comments
Density	1.11 g/cc	0.0401 lb/in ³	ISO 1183
Moisture Absorption at Equilibrium	2.5 - 3.3 %	2.5 - 3.3 %	23°C/50%RH; DIN 53495
Linear Mold Shrinkage	0.0080 - 0.012 cm/cm @Thickness 4.00 mm	0.0080 - 0.012 in/in @Thickness 0.157 in	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	65.0 MPa	9430 psi	50 mm/min; ISO 527
Elongation at Break	>= 50 %	>= 50 %	50 mm/min; ISO 527
Elongation at Yield	4.5 %	4.5 %	50 mm/min; ISO 527
Tensile Modulus	2.40 GPa	348 ksi	ISO 527
Flexural Modulus	1.90 GPa	276 ksi	DIN 52457
Charpy Impact Unnotched	NB @Temperature 23.0 °C	NB @Temperature 73.4 °F	ISO 179
Charpy Impact, Notched	1.30 J/cm ² @Temperature 23.0 °C	6.19 ft-lb/in ² @Temperature 73.4 °F	ISO 179

Thermal Properties	Metric	English	Comments
CTE, linear	90.0 µm/m-°C @Temperature 23.0 - 80.0 °C	50.0 µin/in-°F @Temperature 73.4 - 176 °F	DIN 53752
Melting Point	215 °C	419 °F	Kofler
Deflection Temperature at 0.46 MPa (66 psi)	130 °C	266 °F	ISO 179
Deflection Temperature at 1.8 MPa (264 psi)	50.0 °C	122 °F	ISO 179

Thermal Properties Vicat Softening Point	Metric 170 °C	English 338 °F	Comments 50 N; ISO 306
Flammability, UL94	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	Stufe; IEC 707
	HB @Thickness 3.20 mm	HB @Thickness 0.126 in	Stufe; IEC 707

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 93
Surface Resistance	1.00e+13 ohm	1.00e+13 ohm	ISO 3915
Dielectric Constant	3.5 @Frequency 1e+6 Hz	3.5 @Frequency 1e+6 Hz	IEC 250
Dielectric Strength	30.0 kV/mm	762 kV/in	IEC 243-1
Dielectric Loss Index	0.020	0.020	At 1 MHz; IEC 250
Comparative Tracking Index	600 V	600 V	Stufe; IEC 112

Processing Properties	Metric	English	Comments
Melt Temperature	245 - 260 °C	473 - 500 °F	
Mold Temperature	40.0 - 80.0 °C	104 - 176 °F	

Descriptive Properties	Value	Comments
Back Pressure	Low	
Holding Pressure	High	
Injection Speed	Medium	
Screw Speed	Medium	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China