

CP-Polymer-Technik Wellamid® 6600 CF30 HWCP 30% Carbon Fiber Nylon 66, Heat Stabilized, Conditioned

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66 , 30% Carbon Fiber Filled

Material Notes:

Information provided by CP-Polymer-Technik GmbH & Co. KG

Order this product through the following link:

http://www.lookpolymers.com/polymer_CP-Polymer-Technik-Wellamid-6600-CF30-HWCP-30-Carbon-Fiber-Nylon-66-Heat-Stabilized-Conditioned.php

Physical Properties	Metric	English	Comments
Density	1.35 g/cc	0.0488 lb/in ³	ISO 1183
Moisture Absorption at Equilibrium	1.8 - 2.3 %	1.8 - 2.3 %	23°C/50%RH, Starting when dry; DIN 53495
Linear Mold Shrinkage	0.0020 cm/cm @Thickness 4.00 mm	0.0020 in/in @Thickness 0.157 in	
Linear Mold Shrinkage, Transverse	0.0070 cm/cm @Thickness 4.00 mm	0.0070 in/in @Thickness 0.157 in	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	145 MPa	21000 psi	5 mm/min; ISO 527
Elongation at Break	3.5 %	3.5 %	5 mm/min; ISO 527
Tensile Modulus	16.0 GPa	2320 ksi	ISO 527
Charpy Impact Unnotched	7.80 J/cm ² @Temperature 23.0 °C	37.1 ft-lb/in ² @Temperature 73.4 °F	ISO 179
Charpy Impact, Notched	1.80 J/cm ² @Temperature 23.0 °C	8.57 ft-lb/in ² @Temperature 73.4 °F	ISO 179

Thermal Properties	Metric	English	Comments
Melting Point	255 °C	491 °F	Kofler

Processing Properties	Metric	English	Comments
Melt Temperature	275 - 295 °C	527 - 563 °F	
Mold Temperature	80.0 - 100 °C	176 - 212 °F	

Descriptive Properties	Value	Comments
Back Pressure	Low	
Holding Pressure	High	
Injection Speed	High	
Screw Speed	High	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China