

CP-Polymer-Technik Wellamid® 6600 GS 40 HWCP 40% Glass Sphere Filled Nylon 66, Heat Stabilized, Conditioned

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, Glass Bead Filled

Material Notes:

Information provided by CP-Polymer-Technik GmbH & Co. KG

Order this product through the following link:

http://www.lookpolymers.com/polymer_CP-Polymer-Technik-Wellamid-6600-GS-40-HWCP-40-Glass-Sphere-Filled-Nylon-66-Heat-Stabilized-Conditioned.php

Physical Properties	Metric	English	Comments
Density	1.46 g/cc	0.0527 lb/in ³	ISO 1183
Moisture Absorption at Equilibrium	1.8 - 2.3 %	1.8 - 2.3 %	23°C/50%RH, Starting when dry; DIN 53495
Linear Mold Shrinkage	0.0090 - 0.011 cm/cm @Thickness 4.00 mm	0.0090 - 0.011 in/in @Thickness 0.157 in	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	60.0 MPa	8700 psi	5 mm/min; ISO 527
Elongation at Break	15 %	15 %	5 mm/min; ISO 527
Tensile Modulus	2.60 GPa	377 ksi	ISO 527
Charpy Impact Unnotched	6.00 J/cm ² @Temperature 23.0 °C	28.6 ft-lb/in ² @Temperature 73.4 °F	ISO 179
Charpy Impact, Notched	1.80 J/cm ² @Temperature 23.0 °C	8.57 ft-lb/in ² @Temperature 73.4 °F	ISO 179

Thermal Properties	Metric	English	Comments
Melting Point	255 °C	491 °F	Kofler

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+12 ohm-cm	1.00e+12 ohm-cm	IEC 93
Surface Resistance	1.00e+10 ohm	1.00e+10 ohm	ISO 3915
Dielectric Constant	6.0 @Frequency 1e+6 Hz	6.0 @Frequency 1e+6 Hz	IEC 250
Dielectric Strength	35.0 kV/mm	889 kV/in	IEC 243-1

Electrical Properties	Metric	English	Comments TC 250
-----------------------	--------	---------	-----------------

Processing Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Melt Temperature	265 - 290 °C	509 - 554 °F	
Mold Temperature	70.0 - 100 °C	158 - 212 °F	

Descriptive Properties	Value	Comments
------------------------	-------	----------

Back Pressure	Low	
Holding Pressure	High	
Injection Speed	Medium to High	
Screw Speed	Medium	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China