

## CP-Polymer-Technik Wellamid® 6600 GV 30 HW 30% Glass Fiber Nylon 66, Heat Stabilized, Dry

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 30% Glass Fiber Filled

### Material Notes:

Information provided by CP-Polymer-Technik GmbH & Co. KG

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_CP-Polymer-Technik-Wellamid-6600-GV-30-HW-30-Glass-Fiber-Nylon-66-Heat-Stabilized-Dry.php](http://www.lookpolymers.com/polymer_CP-Polymer-Technik-Wellamid-6600-GV-30-HW-30-Glass-Fiber-Nylon-66-Heat-Stabilized-Dry.php)

Physical Properties	Metric	English	Comments
Density	1.36 g/cc	0.0491 lb/in <sup>3</sup>	ISO 1183
Moisture Absorption at Equilibrium	1.8 - 2.3 %	1.8 - 2.3 %	23°C/50%RH; DIN 53495
Linear Mold Shrinkage	0.0020 cm/cm	0.0020 in/in	
	@Thickness 4.00 mm	@Thickness 0.157 in	
Linear Mold Shrinkage, Transverse	0.0070 cm/cm	0.0070 in/in	
	@Thickness 4.00 mm	@Thickness 0.157 in	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	170 MPa	24700 psi	5 mm/min; ISO 527
Elongation at Break	2.5 %	2.5 %	5 mm/min; ISO 527
Tensile Modulus	8.50 GPa	1230 ksi	ISO 527
Flexural Modulus	7.00 GPa	1020 ksi	DIN 52457
Charpy Impact Unnotched	6.00 J/cm <sup>2</sup>	28.6 ft-lb/in <sup>2</sup>	ISO 179
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	0.800 J/cm <sup>2</sup>	3.81 ft-lb/in <sup>2</sup>	ISO 179
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
CTE, linear	20.0 µm/m-°C	11.1 µin/in-°F	
	@Temperature 23.0 - 80.0 °C	@Temperature 73.4 - 176 °F	DIN 53752
Melting Point	255 °C	491 °F	Kofler
Deflection Temperature at 0.46 MPa (66 psi)	250 °C	482 °F	ISO 179
Deflection Temperature at 1.8 MPa	250 °C	482 °F	

(264 psi) Thermal Properties	Metric	English	ISO 179 Comments
Vicat Softening Point	220 °C	428 °F	50 N; ISO 306
Flammability, UL94	HB	HB	Stufe; IEC 707
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	HB	HB	Stufe; IEC 707
	@Thickness 3.20 mm	@Thickness 0.126 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 93
Surface Resistance	1.00e+12 ohm	1.00e+12 ohm	ISO 3915
Dielectric Constant	4.0	4.0	IEC 250
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dielectric Strength	40.0 kV/mm	1020 kV/in	IEC 243-1
Dielectric Loss Index	0.015	0.015	At 1 MHz; IEC 250
Comparative Tracking Index	550 V	550 V	Stufe; IEC 112

Processing Properties	Metric	English	Comments
Melt Temperature	265 - 295 °C	509 - 563 °F	
Mold Temperature	70.0 - 100 °C	158 - 212 °F	

Descriptive Properties	Value	Comments
Back Pressure	Low	
Holding Pressure	High	
Injection Speed	High	
Screw Speed	Medium	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China