

CP-Polymer-Technik Wellamid® 6600/58 HWCP Nylon 66, Impact Modified Until -40°C, Heat Stabilized, Dry

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, Impact Grade

Material Notes:

Information provided by CP-Polymer-Technik GmbH & Co. KG

Order this product through the following link:

http://www.lookpolymers.com/polymer_CP-Polymer-Technik-Wellamid-660058-HWCP-Nylon-66-Impact-Modified-Until-40C-Heat-Stabilized-Dry.php

Physical Properties	Metric	English	Comments
Density	1.07 g/cc	0.0387 lb/in ³	ISO 1183
Moisture Absorption at Equilibrium	2.5 - 3.0 %	2.5 - 3.0 %	23°C/50%RH; DIN 53495
Linear Mold Shrinkage	0.0080 - 0.012 cm/cm @Thickness 4.00 mm	0.0080 - 0.012 in/in @Thickness 0.157 in	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	55.0 MPa	7980 psi	50 mm/min; ISO 527
Elongation at Break	>= 50 %	>= 50 %	50 mm/min; ISO 527
Elongation at Yield	5.0 %	5.0 %	50 mm/min; ISO 527
Tensile Modulus	2.30 GPa	334 ksi	ISO 527
Flexural Modulus	1.90 GPa	276 ksi	DIN 52457
Charpy Impact Unnotched	NB	NB	ISO 179
	@Temperature -40.0 °C	@Temperature -40.0 °F	
Charpy Impact Unnotched	NB	NB	ISO 179
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	NB	NB	ISO 179
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
CTE, linear	90.0 µm/m-°C	50.0 µin/in-°F	DIN 53752
	@Temperature 23.0 - 80.0 °C	@Temperature 73.4 - 176 °F	
Melting Point	255 °C	491 °F	Kofler

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	65.0 °C	149 °F	ISO 179
Vicat Softening Point	200 °C	392 °F	50 N; ISO 306
Flammability, UL94	HB	HB	Stufe; IEC 707
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	HB	HB	Stufe; IEC 707
	@Thickness 3.20 mm	@Thickness 0.126 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 93
Surface Resistance	1.00e+13 ohm	1.00e+13 ohm	ISO 3915
Dielectric Constant	3.4	3.4	IEC 250
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dielectric Strength	30.0 kV/mm	762 kV/in	IEC 243-1
Dielectric Loss Index	0.015	0.015	At 1 MHz; IEC 250
Comparative Tracking Index	600 V	600 V	Stufe; IEC 112

Processing Properties	Metric	English	Comments
Melt Temperature	260 - 280 °C	500 - 536 °F	
Mold Temperature	50.0 - 90.0 °C	122 - 194 °F	

Descriptive Properties	Value	Comments
Back Pressure	Low	
Holding Pressure	High	
Injection Speed	Medium to High	
Screw Speed	Medium	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China