

CTC SunPro® SP 200 P4058 Polypropylene Copolymer

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene Copolymer

Material Notes:

SunPro® SP 200 P 4058 is a general purpose, medium flow, polypropylene copolymer. It has applications in automotive wheel housings and general purpose automotive. Automotive Certifications: Chrysler MS DB 543, CPN 4058 Data provided by Composite Technologies (CTC).

Order this product through the following link:

http://www.lookpolymers.com/polymer_CTC-SunPro-SP-200-P4058-Polypropylene-Copolymer.php

Physical Properties	Metric	English	Comments
Melt Flow	17 g/10 min	17 g/10 min	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	24.0 MPa	3480 psi	ISO 527-1/2
Flexural Modulus	0.875 GPa	127 ksi	ISO 178
Izod Impact, Notched (ISO)	8.00 kJ/m ²	3.81 ft-lb/in ²	Low Temp; ISO 180/A

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	182 - 216 °C	360 - 420 °F	
Middle Barrel Temperature	193 - 227 °C	380 - 440 °F	
Front Barrel Temperature	204 - 216 °C	400 - 420 °F	
Nozzle Temperature	204 - 216 °C	400 - 420 °F	
Melt Temperature	204 - 227 °C	400 - 440 °F	
Mold Temperature	26.7 - 60.0 °C	80.0 - 140 °F	
Back Pressure	0.345 - 1.03 MPa	50.0 - 150 psi	
Clamp Pressure	27.6 - 34.5 MPa	4000 - 5000 psi	

Descriptive Properties	Value	Comments
Boost Pressure (psi)	500-1500	
Hold Pressure	50 - 75% of Boost	
Screw Speed	Medium to Fast	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China