

## California Fine Wire Nickel Alloy 60 Copper Nickel Resistance Wire

Category : Metal , Electronic/Magnetic Alloy , Nonferrous Metal , Copper Alloy

### Material Notes:

All values may vary dependent on specific design and usage Capabilities: WireRibbonSquareInsulatedPlated Information provided by California Fine Wire.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_California-Fine-Wire-Nickel-Alloy-60-Copper-Nickel-Resistance-Wire.php](http://www.lookpolymers.com/polymer_California-Fine-Wire-Nickel-Alloy-60-Copper-Nickel-Resistance-Wire.php)

Physical Properties	Metric	English	Comments
Density	8.89 g/cc	0.321 lb/in <sup>3</sup>	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	241 MPa	35000 psi	Annealed
	483 MPa	70000 psi	Hard

Thermal Properties	Metric	English	Comments
CTE, linear	16.2 $\mu\text{m}/\text{m}\cdot\text{C}$	9.00 $\mu\text{in}/\text{in}\cdot\text{F}$	
	@Temperature 20.0 $^{\circ}\text{C}$	@Temperature 68.0 $^{\circ}\text{F}$	
Specific Heat Capacity	0.385 J/g- $^{\circ}\text{C}$	0.0920 BTU/lb- $^{\circ}\text{F}$	
	@Temperature 20.0 $^{\circ}\text{C}$	@Temperature 68.0 $^{\circ}\text{F}$	
Thermal Conductivity	90.0 W/m-K	625 BTU-in/hr-ft <sup>2</sup> - $^{\circ}\text{F}$	
Melting Point	1100 $^{\circ}\text{C}$	2012 $^{\circ}\text{F}$	
Maximum Service Temperature, Air	600 $^{\circ}\text{C}$	1110 $^{\circ}\text{F}$	Operating Temperature

Component Elements Properties	Metric	English	Comments
Copper, Cu	94 %	94 %	
Nickel, Ni	6.0 %	6.0 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.00000997 ohm-cm	0.00000997 ohm-cm	3% tolerance on sizes below 0.02, 5% tolerance on sizes above 0.02

Descriptive Properties	Value	Comments
Magnetic	None	

Temperature Coefficient of Resistance Descriptive Properties	0.0005 ohms/ohm- °C Value	0- 100°C Comments
Thermal EMF vs. Copper	-0.022	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China