

## Carmel Olefins CAPILENE® T 50 Polypropylene Homopolymer

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Molded

### Material Notes:

CAPILENE® T 50 is a high melt flow rate homopolymer for injection molding characterized by good flow properties combined with good stiffness. APPLICATIONS CAPILENE® T 50 is recommended for injection molding of household articles, closures, crates, containers and garden furniture.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Carmel-Olefins-CAPILENE-T-50-Polypropylene-Homopolymer.php](http://www.lookpolymers.com/polymer_Carmel-Olefins-CAPILENE-T-50-Polypropylene-Homopolymer.php)

Physical Properties	Metric	English	Comments
Melt Flow	25 g/10 min @Load 2.16 kg, Temperature 230 °C	25 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	32.0 MPa	4640 psi	ASTM D638
Elongation at Yield	12 %	12 %	ASTM D638
Flexural Modulus	1.45 GPa	210 ksi	ASTM D790
Izod Impact, Notched	0.230 J/cm @Temperature >=23.0 °C	0.431 ft-lb/in @Temperature >=73.4 °F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	97.0 °C	207 °F	ASTM D648
Vicat Softening Point	155 °C @Load 1.02 kg	311 °F @Load 2.25 lb	ASTM D1525

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China