

Carmel Olefins IPETHENE® 830 Low Density Polyethylene

Category : Polymer , Thermoplastic , Polyethylene (PE) , LDPE , Low Density Polyethylene (LDPE), Molded

Material Notes:

IPETHENE® 830 is a low density polyethylene injection molding grade. It exhibits high melt flow rate and high stiffness. APPLICATIONS

IPETHENE® 830 is used to produce lids, containers, toys, and domestic hollowware.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Carmel-Olefins-IPETHENE-830-Low-Density-Polyethylene.php

Physical Properties	Metric	English	Comments
Density	0.920 g/cc	0.0332 lb/in ³	ISO 1183-A
Melt Flow	20 g/10 min @Load 2.16 kg, Temperature 190 °C	20 g/10 min @Load 4.76 lb, Temperature 374 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	11.5 MPa	1670 psi	ISO 527-2
Tensile Strength, Yield	11.5 MPa	1670 psi	ISO 527-2
Elongation at Break	80 %	80 %	ISO 527-2

Thermal Properties	Metric	English	Comments
Vicat Softening Point	91.0 °C @Load 1.02 kg	196 °F @Load 2.25 lb	ISO 306

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China