

Carpenter Gall-Tough PLUS™ Stainless, Annealed, 25% Cold Work

Category : Metal , Ferrous Metal , Stainless Steel

Material Notes:

Data provided by Carpenter Technology Corporation. Annealed 1150°C, water quenched, and cold drawn. Threshold Galling Stress 48 MPa. The avg. total volume loss on the wear test is 10.6 mm³ at 100 rpm. Gall-Tough PLUS™ stainless is a high silicon, high manganese, nitrogen strengthened, austenitic stainless alloy which exhibits superior self-mated galling resistance and metal-to-metal wear resistance. The alloy possesses higher strength than Type 316. It also exhibits chloride corrosion resistance equal to or better than Type 316, along with equivalent high temperature oxidation resistance. Gall-Tough PLUS™ is a trademark of Carpenter Technology Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Carpenter-Gall-Tough-PLUS-Stainless-Annealed-25-Cold-Work.php

Physical Properties	Metric	English	Comments
Density	7.60 g/cc	0.275 lb/in ³	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	1027 MPa	149000 psi	
	1268 MPa @Temperature -73.0 °C	183900 psi @Temperature -99.4 °F	
Tensile Strength, Yield	744 MPa @Strain 0.200 %	108000 psi @Strain 0.200 %	
	937 MPa @Strain 0.200 %, Temperature -73.0 °C	136000 psi @Strain 0.200 %, Temperature -99.4 °F	
Elongation at Break	30 %	30 %	in 4D
	31 % @Temperature -73.0 °C	31 % @Temperature -99.4 °F	in 4D
Reduction of Area	65 %	65 %	
Modulus of Elasticity	184.9 GPa	26820 ksi	

Thermal Properties	Metric	English	Comments
CTE, linear	14.19 µm/m-°C	7.883 µin/in-°F	
	@Temperature 25.0 - 50.0 °C	@Temperature 77.0 - 122 °F	
	17.1 µm/m-°C	9.48 µin/in-°F	

Thermal Properties	@Temperature 25.0 - Metric 250 °C	@Temperature 77.0 - English 480 °F	Comments
	18.07 $\mu\text{m}/\text{m}\cdot\text{°C}$	10.04 $\mu\text{in}/\text{in}\cdot\text{°F}$	
	@Temperature 25.0 - 500 °C	@Temperature 77.0 - 932 °F	
Specific Heat Capacity	0.5055 J/g·°C	0.1208 BTU/lb·°F	
	@Temperature 50.0 - 100 °C	@Temperature 122 - 212 °F	
Thermal Conductivity	12.0 W/m-K	83.3 BTU-in/hr-ft ² -°F	
Maximum Service Temperature, Air	982 °C	1800 °F	Scaling Temperature for Continuous Service

Component Elements Properties	Metric	English	Comments
Carbon, C	<= 0.15 %	<= 0.15 %	
Chromium, Cr	16.5 - 21 %	16.5 - 21 %	
Iron, Fe	62 %	62 %	as remainder
Manganese, Mn	4.0 - 8.0 %	4.0 - 8.0 %	
Molybdenum, Mo	0.50 - 2.5 %	0.50 - 2.5 %	
Nickel, Ni	6.0 - 10 %	6.0 - 10 %	
Nitrogen, N	0.050 - 0.35 %	0.050 - 0.35 %	
Phosphorous, P	<= 0.040 %	<= 0.040 %	
Silicon, Si	2.5 - 4.5 %	2.5 - 4.5 %	
Sulfur, S	<= 0.040 %	<= 0.040 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.0000947 ohm-cm	0.0000947 ohm-cm	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China