

Carpenter Gall-Tough® Stainless, Annealed and Cold Drawn Bar, 0% Cold Work

Category : Metal , Ferrous Metal , Stainless Steel , T S20000 Series Stainless Steel

Material Notes:

Data provided by Carpenter Technology Corporation. Threshold Galling Stress 103 MPa (higher stress tests not performed). The avg. total volume loss on the wear test is 5 mm³ at 100 rpm. Gall-Tough® stainless is a high silicon, high manganese, nitrogen strengthened, austenitic stainless alloy which possesses superior self-mated galling resistance and metal-to-metal wear resistance. The alloy possesses higher strength and high temperature oxidation resistance than Type 304 stainless with comparable corrosion resistance, depending on the environment. Gall-Tough® is a registered trademark of Carpenter Technology Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Carpenter-Gall-Tough-Stainless-Annealed-and-Cold-Drawn-Bar-0-Cold-Work.php

Physical Properties	Metric	English	Comments
Density	7.85 g/cc	0.284 lb/in ³	
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	979 MPa	142000 psi	
	1344 MPa	194900 psi	
	@Temperature -73.0 °C	@Temperature -99.4 °F	
Tensile Strength, Yield	379 MPa	55000 psi	
	@Strain 0.200 %	@Strain 0.200 %	
	448 MPa	65000 psi	
	@Strain 0.200 %, Temperature -73.0 °C	@Strain 0.200 %, Temperature -99.4 °F	
Elongation at Break	59 %	59 %	in 4D
	47 %	47 %	in 4D
	@Temperature -73.0 °C	@Temperature -99.4 °F	
Reduction of Area	59 %	59 %	
	68 %	68 %	
	@Temperature -73.0 °C	@Temperature -99.4 °F	
Modulus of Elasticity	171.1 GPa	24820 ksi	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact	325 J	240 ft-lb	V-notch

Thermal Properties	Metric	English	Comments
CTE, linear	17.3 $\mu\text{m}/\text{m}\cdot^{\circ}\text{C}$	9.60 $\mu\text{in}/\text{in}\cdot^{\circ}\text{F}$	
	@Temperature 25.0 - 100 $^{\circ}\text{C}$	@Temperature 77.0 - 212 $^{\circ}\text{F}$	
	17.73 $\mu\text{m}/\text{m}\cdot^{\circ}\text{C}$	9.850 $\mu\text{in}/\text{in}\cdot^{\circ}\text{F}$	
	@Temperature 25.0 - 250 $^{\circ}\text{C}$	@Temperature 77.0 - 482 $^{\circ}\text{F}$	
Specific Heat Capacity	18.5 $\mu\text{m}/\text{m}\cdot^{\circ}\text{C}$	10.3 $\mu\text{in}/\text{in}\cdot^{\circ}\text{F}$	
	@Temperature 25.0 - 500 $^{\circ}\text{C}$	@Temperature 77.0 - 932 $^{\circ}\text{F}$	
Specific Heat Capacity	0.5145 J/g- $^{\circ}\text{C}$	0.1230 BTU/lb- $^{\circ}\text{F}$	
	@Temperature 52.0 - 102 $^{\circ}\text{C}$	@Temperature 126 - 216 $^{\circ}\text{F}$	
Thermal Conductivity	12.22 W/m-K	84.81 BTU-in/hr-ft 2 - $^{\circ}\text{F}$	
	@Temperature 23.0 $^{\circ}\text{C}$	@Temperature 73.4 $^{\circ}\text{F}$	
Maximum Service Temperature, Air	982 $^{\circ}\text{C}$	1800 $^{\circ}\text{F}$	Scaling Temperature for Continuous Service

Component Elements Properties	Metric	English	Comments
Carbon, C	$\leq 0.15\%$	$\leq 0.15\%$	
Chromium, Cr	15 - 18 %	15 - 18 %	
Iron, Fe	68 %	68 %	as remainder
Manganese, Mn	4.0 - 6.0 %	4.0 - 6.0 %	
Molybdenum, Mo	0.50 - 2.5 %	0.50 - 2.5 %	
Nickel, Ni	4.0 - 6.0 %	4.0 - 6.0 %	
Nitrogen, N	0.080 - 0.20 %	0.080 - 0.20 %	
Phosphorous, P	$\leq 0.040\%$	$\leq 0.040\%$	
Silicon, Si	3.0 - 4.0 %	3.0 - 4.0 %	
Sulfur, S	$\leq 0.040\%$	$\leq 0.040\%$	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.0000716 ohm-cm	0.0000716 ohm-cm	
	@Temperature 23.0 $^{\circ}\text{C}$	@Temperature 73.4 $^{\circ}\text{F}$	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China