

Carpenter HyMu "80"® Electronic Alloy, Hydrogen Annealed Strip

Category : Metal , Electronic/Magnetic Alloy , Nonferrous Metal , Nickel Alloy

Material Notes:

Data provided by Carpenter Technology Corporation. Carpenter HyMu "80"® alloy is an unoriented, 80% nickel-iron-molybdenum alloy which offers extremely high initial permeability as well as maximum permeability with minimum hysteresis loss. Carpenter HyMu "80" alloy has been used primarily in transformer cores, tape wound toroids and laminations where compactness and weight factors are important. It has also been used for shielding to protect electrical components from stray magnetic fields. HyMu "80"® is a registered trademark of Carpenter Technology Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Carpenter-HyMu-80-Electronic-Alloy-Hydrogen-Annealed-Strip.php

Physical Properties	Metric	English	Comments
Density	8.74 g/cc	0.316 lb/in ³	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell B	58	58	
Tensile Strength, Ultimate	531 MPa	77000 psi	
Tensile Strength, Yield	145 MPa	21000 psi	Offset not specified
Elongation at Break	38 %	38 %	
Modulus of Elasticity	230 GPa	33400 ksi	Bar
Izod Impact	115 J	84.8 ft-lb	Bar

Thermal Properties	Metric	English	Comments
CTE, linear	12.0 µm/m-°C	6.67 µin/in-°F	
	@Temperature 25.0 - 300 °C	@Temperature 77.0 - 572 °F	
	12.3 µm/m-°C	6.83 µin/in-°F	
	@Temperature 25.0 - 50.0 °C	@Temperature 77.0 - 122 °F	
Specific Heat Capacity	0.494 J/g-°C	0.118 BTU/lb-°F	
Thermal Conductivity	34.6 W/m-K	240 BTU-in/hr-ft ² -°F	
Melting Point	1454 °C	2649 °F	
Solidus	1454 °C	2649 °F	Melting Point
Liquidus	1454 °C	2649 °F	Melting Point

Thermal Properties	Metric	English	Comments
Carbon, C	0.020 %	0.020 %	
Iron, Fe	15 %	15 %	as remainder
Manganese, Mn	0.50 %	0.50 %	
Molybdenum, Mo	4.2 %	4.2 %	
Nickel, Ni	80 %	80 %	
Silicon, Si	0.35 %	0.35 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.0000580 ohm-cm	0.0000580 ohm-cm	Temp Coefficient 0.0011/°C (-17.8-449°C)
Curie Temperature	460 °C	860 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China