

Cathay PA513 Renewable Engineering Polyamide

Category : Polymer , Thermoplastic , Nylon

Material Notes:

Cathay engineering polyamides contain 26- 100% renewably sourced material. Advantages: Operates at similar conditions to PA66;

Suitable for injection, compounding and extrusion; Stable mechanical properties Information provided by Cathay

Order this product through the following link:

http://www.lookpolymers.com/polymer_Cathay-PA513-Renewable-Engineering-Polyamide.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.06 g/cc	1.06 g/cc	ISO 1183
Water Absorption	0.30 %	0.30 %	Equilibrium, 50%RH; ISO 62

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	50.0 MPa	7250 psi	ISO 527-2/1A/50
Elongation at Yield	>= 100 %	>= 100 %	ISO 527-2/1A/50
Tensile Modulus	1.60 GPa	232 ksi	ISO 527-2/1
Flexural Strength	54.0 MPa	7830 psi	ISO 178
Flexural Modulus	1.39 GPa	202 ksi	ISO 178
Izod Impact, Notched (ISO)	8.60 kJ/m ²	4.09 ft-lb/in ²	ISO 180/1A
Charpy Impact, Notched	0.780 J/cm ²	3.71 ft-lb/in ²	ISO 179/1eA

Thermal Properties	Metric	English	Comments
Melting Point	208 °C	406 °F	ISO 3146
Deflection Temperature at 1.8 MPa (264 psi)	50.0 °C	122 °F	ISO 75-2/A

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+13 ohm-cm	1.00e+13 ohm-cm	IEC 60093

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China