

Ceradyne Ceralloy® 147-5 Silicon Nitride

Category : Ceramic , Nitride

Material Notes:

Ceralloy® 147 Hot Pressed Silicon Nitride (HPSN) can be formulated into a variety of compositions having minimal densification aids. These HPSN compositions offer the highest strength of Ceradyne's silicon nitrides. Finished components are machined at Ceradynes precision diamond grinding facility. Applications: wear components. Information provided by Ceradyne Company

Order this product through the following link:

http://www.lookpolymers.com/polymer_Ceradyne-Ceralloy-147-5-Silicon-Nitride.php

Physical Properties	Metric	English	Comments
Density	3.30 g/cc	0.119 lb/in ³	
Weibull Modulus	15 - 20	15 - 20	

Mechanical Properties	Metric	English	Comments
Vickers Microhardness	1800	1800	0.3
Modulus of Elasticity	320 GPa	46400 ksi	
Flexural Strength	930 MPa @Temperature 23.0 °C	135000 psi @Temperature 73.4 °F	
Poissons Ratio	0.28	0.28	
Fracture Toughness	6.00 MPa-m ^{1/2}	5.46 ksi-in ^{1/2}	
Shear Modulus	125 GPa	18100 ksi	calculated
Abrasion	1100	1100	Abrasive Wear Resistance Parameter

Thermal Properties	Metric	English	Comments
CTE, linear	3.20 µm/m-°C @Temperature 20.0 - 1000 °C	1.78 µin/in-°F @Temperature 68.0 - 1830 °F	
Thermal Conductivity	35.0 W/m-K	243 BTU-in/hr-ft ² -°F	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	1.00e+14 ohm-cm	1.00e+14 ohm-cm	
Dielectric Constant	8.14	8.14	

Descriptive Properties	Value	Comments
Purity, %	>98.5	
Thermal Shock Parameter	654°C	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China