

Chang Chun Plastic Longlite PM T308J General Purpose Phenolic Molding Compound

Category : Polymer , Thermoset , Phenolic , Phenolic; Unreinforced; Molded

Material Notes:

ASTM Grade per ASTM D700 is 3. Information provided by Dowell Trading Company Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chang-Chun-Plastic-Longlite-PM-T308J-General-Purpose-Phenolic-Molding-Compound.php

Physical Properties	Metric	English	Comments
Density	1.45 g/cc	0.0524 lb/in ³	ASTM D792
Water Absorption	0.40 %	0.40 %	ASTM D570
Linear Mold Shrinkage	0.0070 cm/cm	0.0070 in/in	Compression; ASTM D955
	0.0090 cm/cm	0.0090 in/in	Transfer; ASTM D955
	0.013 cm/cm	0.013 in/in	Injection; ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	55.0 MPa	7980 psi	ASTM D651
Flexural Yield Strength	81.0 MPa	11700 psi	ASTM D790
Compressive Yield Strength	193 MPa	28000 psi	ASTM D695
Izod Impact, Notched	0.290 J/cm	0.543 ft-lb/in	ASTM D256
Charpy Impact, Notched	0.320 J/cm ²	1.52 ft-lb/in ²	ASTM D256

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	180 °C	356 °F	Two Hour Heat Resistance per ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	160 °C	320 °F	ASTM D648
Flammability, UL94	V-0	V-0	
	@Thickness 3.44 mm	@Thickness 0.135 in	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	1.00e+11 ohm-cm	1.00e+11 ohm-cm	ASTM D257
Insulation Resistance	1.00e+8 ohm	1.00e+8 ohm	After Boiling; ASTM D257

Electrical Properties	1.00e+9 ohm Metric	1.00e+9 ohm English	Normal: ASTM D257 Comments
Dielectric Strength	9.10 kV/mm	231 kV/in	ASTM D149
Comparative Tracking Index	175 - 250 V	175 - 250 V	UL PLC 3

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China