

Chang Chun Plastic PBT3015 15% Glass Fiber Enforced PBT

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), 20% Glass Fiber Filled

Material Notes:

Information provided by Dowell Trading Company Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chang-Chun-Plastic-PBT3015-15-Glass-Fiber-Enforced-PBT.php

Physical Properties	Metric	English	Comments
Density	1.39 - 1.43 g/cc	0.0502 - 0.0517 lb/in ³	ASTM D792
Water Absorption	0.040 %	0.040 %	24 hour immersion; ASTM D570
Linear Mold Shrinkage	0.0040 - 0.020 cm/cm	0.0040 - 0.020 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	93	93	ASTM D785
Tensile Strength, Ultimate	80.0 - 100 MPa	11600 - 14500 psi	ASTM D638
Elongation at Break	4.0 - 5.0 %	4.0 - 5.0 %	ASTM D638
Flexural Yield Strength	130 - 150 MPa	18900 - 21800 psi	ASTM D790
Flexural Modulus	4.00 - 5.00 GPa	580 - 725 ksi	ASTM D790
Izod Impact, Notched	0.500 - 0.700 J/cm @Thickness 6.35 mm	0.937 - 1.31 ft-lb/in @Thickness 0.250 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	50.0 $\mu\text{m}/\text{m}\cdot\text{C}$ @Temperature 20.0 $^{\circ}\text{C}$	27.8 $\mu\text{in}/\text{in}\cdot\text{F}$ @Temperature 68.0 $^{\circ}\text{F}$	ASTM D696
Melting Point	225 $^{\circ}\text{C}$	437 $^{\circ}\text{F}$	DSC
Deflection Temperature at 0.46 MPa (66 psi)	220 $^{\circ}\text{C}$	428 $^{\circ}\text{F}$	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	206 $^{\circ}\text{C}$	403 $^{\circ}\text{F}$	ASTM D648
Flammability, UL94	HB	HB	1/32 in.

Electrical Properties	Metric	English	Comments
Electrical Resistivity	$\geq 1.00\text{e}+16$ ohm-cm	$\geq 1.00\text{e}+16$ ohm-cm	ASTM D257

Surface Resistance Electrical Properties	$\geq 1.00e+14$ ohm Metric	$\geq 1.00e+14$ ohm English	ASTM D257 Comments
Dielectric Constant	3.3 @Frequency 60 Hz	3.3 @Frequency 60 Hz	ASTM D150
Dielectric Strength	20.0 kV/mm @Thickness 2.00 mm	508 kV/in @Thickness 0.0787 in	ASTM D149
Dissipation Factor	0.0010 @Frequency 60 Hz	0.0010 @Frequency 60 Hz	ASTM D150
Arc Resistance	129 sec	129 sec	ASTM D495

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China