

Chang Chun Plastic PBT4115 Fire Retardant & 15% Glass Fiber Enforced Grade PBT

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), Glass Fiber Filled, Flame Retardant

Material Notes:

Information provided by Dowell Trading Company Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chang-Chun-Plastic-PBT4115-Fire-Retardant-15-Glass-Fiber-Enforced-Grade-PBT.php

Physical Properties	Metric	English	Comments
Density	1.50 - 1.52 g/cc	0.0542 - 0.0549 lb/in ³	ASTM D792
Water Absorption	0.030 %	0.030 %	24 hour immersion; ASTM D570
Linear Mold Shrinkage	0.0040 - 0.020 cm/cm	0.0040 - 0.020 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	93	93	ASTM D785
Tensile Strength, Ultimate	90.0 - 110 MPa	13100 - 16000 psi	ASTM D638
Elongation at Break	4.0 - 5.5 %	4.0 - 5.5 %	ASTM D638
Flexural Yield Strength	140 - 180 MPa	20300 - 26100 psi	ASTM D790
Flexural Modulus	4.50 - 6.50 GPa	653 - 943 ksi	ASTM D790
Izod Impact, Notched	0.500 - 0.700 J/cm @Thickness 6.35 mm	0.937 - 1.31 ft-lb/in @Thickness 0.250 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	55.0 $\mu\text{m}/\text{m}\cdot\text{°C}$ @Temperature 20.0 °C	30.6 $\mu\text{in}/\text{in}\cdot\text{°F}$ @Temperature 68.0 °F	ASTM D696
Melting Point	225 °C	437 °F	DSC
Deflection Temperature at 0.46 MPa (66 psi)	220 °C	428 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	205 °C	401 °F	ASTM D648
Flammability, UL94	V-0	V-0	1/32 in.

Electrical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Electrical Resistivity Electrical Properties	$\geq 1.00\text{e}+16$ ohm-cm Metric	$\geq 1.00\text{e}+16$ ohm-cm English	ASTM D257 Comments
Surface Resistance	$\geq 1.00\text{e}+14$ ohm	$\geq 1.00\text{e}+14$ ohm	ASTM D257
Dielectric Constant	3.3 @Frequency 60 Hz	3.3 @Frequency 60 Hz	ASTM D150
Dielectric Strength	22.0 kV/mm @Thickness 2.00 mm	559 kV/in @Thickness 0.0787 in	ASTM D149
Dissipation Factor	0.0010 @Frequency 60 Hz	0.0010 @Frequency 60 Hz	ASTM D150
Arc Resistance	90 sec	90 sec	ASTM D495

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China