

## Channel Industries 5600 Lead Zirconate Titanate Piezoelectric

Category : Ceramic , Oxide , Zirconium Oxide , Piezoelectric

### Material Notes:

Navy Type V Characterized by high coupling factors and high piezoelectric and dielectric constants over extended temperature ranges and stress amplitudes, lead zirconate titanates are the most extensively used material for electro-mechanical and electro-acoustic transducers. Uses of this grade include: Hydrophones Data provided by Channel Industries, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Channel-Industries-5600-Lead-Zirconate-Titanate-Piezoelectric.php](http://www.lookpolymers.com/polymer_Channel-Industries-5600-Lead-Zirconate-Titanate-Piezoelectric.php)

Physical Properties	Metric	English	Comments
Density	>= 7.50 g/cc	>= 0.271 lb/in <sup>3</sup>	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	28.0 MPa	4060 psi	Dynamic tensile strength
	76.0 MPa	11000 psi	Static

Electrical Properties	Metric	English	Comments
Curie Temperature	>= 240 °C	>= 464 °F	
Dielectric Constant	2400	2400	$K_{T>1}$
	2600	2600	Free dielectric constant $K_{T>3}$
Dissipation Factor	0.020	0.020	Low Field
Piezoelectric Longitudinal Coupling Factor, k <sub>33</sub>	0.73	0.73	
Piezoelectric Transverse Voltage Coefficient, d <sub>31</sub> , 10 <sup>-12</sup> m/V	-225	-225	
Piezoelectric Shear Charge Coefficient, d <sub>15</sub> , 10 <sup>-12</sup> m/V	670	670	
Piezoelectric Longitudinal Voltage Coefficient, g <sub>33</sub> , 10 <sup>-3</sup> V-m/N	22	22	
Piezoelectric Planar Coupling Factor, k <sub>p</sub>	-0.620	-0.620	
Piezoelectric Mechanical Q	70	70	
Piezoelectric Shear Coupling Factor, k <sub>15</sub>	0.68	0.68	
Piezoelectric Longitudinal Charge Coefficient, d <sub>33</sub> , 10 <sup>-12</sup> m/V	505	505	

Electrical Properties Piezoelectric Transverse Voltage Coefficient, $g_{15}$ , $10^{-3}$ V-m/N	Metric	English	Comments
Piezoelectric Shear Voltage Coefficient, $g_{15}$ , $10^{-3}$ V-m/N	31.5	31.5	
Piezoelectric Transverse Coupling Factor, $k_{31}$	-0.360	-0.360	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China