

## Chase Plastics CP Pryme® A110 ABS, 10% Glass Fiber Reinforced

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), 10% Glass Fiber Filled

**Material Notes:**

Features: Glass fiber reinforcement Injection molding Form: Pellets Information provided by Chase Plastics.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Chase-Plastics-CP-Pryme-A110-ABS-10-Glass-Fiber-Reinforced.php](http://www.lookpolymers.com/polymer_Chase-Plastics-CP-Pryme-A110-ABS-10-Glass-Fiber-Reinforced.php)

Physical Properties	Metric	English	Comments
Density	1.10 g/cc	0.0397 lb/in <sup>3</sup>	ASTM D792
Filler Content	10 %	10 %	
Linear Mold Shrinkage, Flow	0.0030 cm/cm	0.0030 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	60.0 MPa	8700 psi	ASTM D638
Elongation at Break	3.0 %	3.0 %	ASTM D638
Flexural Modulus	4.83 GPa	700 ksi	ASTM D790
Izod Impact, Notched	0.587 J/cm	1.10 ft-lb/in	0.125 in; ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	104 °C	220 °F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	98.9 °C	210 °F	Unannealed; ASTM D648

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China