

## Chase Plastics CP Pryme® AC125G Acetal Copolymer, 25% Glass Fiber Reinforced

Category : Polymer , Thermoplastic , Acetal (POM) , Acetal Copolymer, 30% Glass Fiber Reinforced

**Material Notes:**

Information provided by Chase Plastics.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Chase-Plastics-CP-Pryme-AC125G-Acetal-Copolymer-25-Glass-Fiber-Reinforced.php](http://www.lookpolymers.com/polymer_Chase-Plastics-CP-Pryme-AC125G-Acetal-Copolymer-25-Glass-Fiber-Reinforced.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.58 g/cc	1.58 g/cc	ASTM D792
Water Absorption	0.18 %	0.18 %	24 hours; ASTM D570

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	128 MPa	18500 psi	ASTM D638
Elongation at Break	3.0 %	3.0 %	ASTM D638
Flexural Strength	193 MPa	28000 psi	ASTM D790
Flexural Modulus	7.58 GPa	1100 ksi	ASTM D790
Izod Impact, Notched	0.534 J/cm	1.00 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	164 °C @Thickness 3.17 mm	327 °F @Thickness 0.125 in	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	163 °C @Thickness 3.17 mm	325 °F @Thickness 0.125 in	Unannealed; ASTM D648

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China