

Chase Plastics CP Pryme® N140MGHSL (COND, 50% RH) Nylon 6, 40% Mineral/Glass Reinforced, Heat Stabilized, Internally Lubricated

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , Glass/Mineral Reinforced

Material Notes:

Information provided by Chase Plastics.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chase-Plastics-CP-Pryme-N140MGHSL-COND-50-RH-Nylon-6-40-MineralGlass-Reinforced-Heat-Stabilized-Internally-Lubricated.php

| Mechanical Properties | Metric | English | Comments |
|---------------------------|-----------|---------------|-----------|
| Tensile Strength at Break | 67.0 MPa | 9720 psi | ASTM D638 |
| Flexural Strength | 115.4 MPa | 16740 psi | ASTM D790 |
| Flexural Modulus | 5.10 GPa | 740 ksi | ASTM D790 |
| Izod Impact, Notched | 1.60 J/cm | 3.00 ft-lb/in | ASTM D256 |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China