

Chase Plastics CP Pryme® N213GL (COND, 50% RH) Nylon 6, 13% Glass Fiber Reinforced, Internally Lubricated

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, Glass Fiber/Solid Lube Filled

Material Notes:

Information provided by Chase Plastics.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chase-Plastics-CP-Pryme-N213GL-COND-50-RH-Nylon-6-13-Glass-Fiber-Reinforced-Internally-Lubricated.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.23 g/cc	1.23 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	59.3 MPa	8600 psi	ASTM D638
Flexural Strength	84.1 MPa	12200 psi	ASTM D790
Flexural Modulus	2.24 GPa	325 ksi	ASTM D790
Izod Impact, Notched	1.60 J/cm	3.00 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	210 °C	410 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	191 °C	375 °F	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China