

Chase Plastics CP Pryme® N300STL (COND, 50% RH) Nylon 6 (Utility Grade), Super Toughened, Internally Lubricated

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , Impact Grade

Material Notes:

Information provided by Chase Plastics.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chase-Plastics-CP-Pryme-N300STL-COND-50-RH-Nylon-6-Utility-Grade-Super-Toughened-Internally-Lubricated.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.06 g/cc	1.06 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	26.9 MPa	3900 psi	ASTM D638
Flexural Strength	24.8 MPa	3600 psi	ASTM D790
Flexural Modulus	0.621 GPa	90.0 ksi	ASTM D790
Izod Impact, Notched	52.9 J/cm	99.0 ft-lb/in	ASTM D256

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China