

## Chase Plastics CP Pryme® N320GL (COND, 50% RH) Nylon 6 (Utility Grade), 20% Glass Fiber Reinforced, Internally Lubricated

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , 20% Glass Fiber Filled

**Material Notes:**

Information provided by Chase Plastics.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Chase-Plastics-CP-Pryme-N320GL-COND-50-RH-Nylon-6-Utility-Grade-20-Glass-Fiber-Reinforced-Internally-Lubricated.php](http://www.lookpolymers.com/polymer_Chase-Plastics-CP-Pryme-N320GL-COND-50-RH-Nylon-6-Utility-Grade-20-Glass-Fiber-Reinforced-Internally-Lubricated.php)

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	69.6 MPa	10100 psi	ASTM D638
Flexural Strength	104 MPa	15100 psi	ASTM D790
Flexural Modulus	3.40 GPa	493 ksi	ASTM D790
Izod Impact, Notched	1.76 J/cm	3.30 ft-lb/in	ASTM D256

### Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China