

Chase Plastics CP Pryme® N330L (Dry) Nylon 6, 30% Glass Fiber Reinforced, Lubricated, Recycled Content

Category : Polymer , Renewable/Recycled Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, 30% Glass Fiber Filled

Material Notes:

Features: Lubricated Recycled content Form: Pellets Information provided by Chase Plastics.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chase-Plastics-CP-Pryme-N330L-Dry-Nylon-6-30-Glass-Fiber-Reinforced-Lubricated-Recycled-Content.php

Physical Properties	Metric	English	Comments
Density	1.40 g/cc	0.0506 lb/in ³	ASTM D792
Filler Content	30 %	30 %	
Water Absorption	1.4 %	1.4 %	At 24 hrs; ASTM D570
Linear Mold Shrinkage, Flow	0.0030 cm/cm	0.0030 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	165 MPa	24000 psi	ASTM D638
Elongation at Break	1.8 %	1.8 %	ASTM D638
Flexural Strength	255 MPa	37000 psi	ASTM D790
Flexural Modulus	8.27 GPa	1200 ksi	ASTM D790
Izod Impact, Notched	1.01 J/cm	1.90 ft-lb/in	0.125 in; ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	216 °C	420 °F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	210 °C	410 °F	Unannealed; ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China