

## Chase Plastics CP Pryme® N333GL (DAM) Nylon 6 (Utility Grade), 33% Glass Fiber Reinforced, Internally Lubricated

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , 30% Glass Fiber Filled

### Material Notes:

Information provided by Chase Plastics.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Chase-Plastics-CP-Pryme-N333GL-DAM-Nylon-6-Utility-Grade-33-Glass-Fiber-Reinforced-Internally-Lubricated.php](http://www.lookpolymers.com/polymer_Chase-Plastics-CP-Pryme-N333GL-DAM-Nylon-6-Utility-Grade-33-Glass-Fiber-Reinforced-Internally-Lubricated.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.39 g/cc	1.39 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	134 MPa	19500 psi	ASTM D638
Elongation at Break	2.0 %	2.0 %	ASTM D638
Flexural Strength	207 MPa	30000 psi	ASTM D790
Flexural Modulus	8.62 GPa	1250 ksi	ASTM D790
Izod Impact, Notched	1.28 J/cm	2.40 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	204 °C	400 °F	ASTM D648

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China