

Chase Plastics CP Pryme® NN100HL (Dry) Nylon 66, Heat Stabilized, Lubricated

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, Heat Stabilized

Material Notes:

Features: Heat StabilizedLubricatedForm: PelletsInformation provided by Chase Plastics.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chase-Plastics-CP-Pryme-NN100HL-Dry-Nylon-66-Heat-Stabilized-Lubricated.php

Physical Properties	Metric	English	Comments
Density	1.13 g/cc	0.0408 lb/in ³	ASTM D792
Water Absorption	1.2 %	1.2 %	At 24 hrs; ASTM D570
Linear Mold Shrinkage, Flow	0.015 cm/cm	0.015 in/in	0.125 in; ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	121	121	ASTM D785
Tensile Strength at Break	82.7 MPa	12000 psi	ASTM D638
Elongation at Break	50 %	50 %	ASTM D638
Flexural Strength	96.5 MPa	14000 psi	ASTM D790
Izod Impact, Notched	0.534 J/cm	1.00 ft-lb/in	0.125 in; ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	256 °C	493 °F	
Deflection Temperature at 1.8 MPa (264 psi)	82.2 °C	180 °F	Unannealed; ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China