

## Chase Plastics CP Pryme® NN113GL (DAM) Nylon 66, 13% Glass Fiber Reinforced, Internally Lubricated

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66 , 10% Glass Fiber Filled

**Material Notes:**

Information provided by Chase Plastics.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Chase-Plastics-CP-Pryme-NN113GL-DAM-Nylon-66-13-Glass-Fiber-Reinforced-Internally-Lubricated.php](http://www.lookpolymers.com/polymer_Chase-Plastics-CP-Pryme-NN113GL-DAM-Nylon-66-13-Glass-Fiber-Reinforced-Internally-Lubricated.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.22 g/cc	1.22 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	117 MPa	17000 psi	ASTM D638
Elongation at Break	4.0 %	4.0 %	ASTM D638
Flexural Strength	165 MPa	24000 psi	ASTM D790
Flexural Modulus	4.65 GPa	675 ksi	ASTM D790
Izod Impact, Notched	0.481 J/cm	0.900 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	254 °C	490 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	235 °C	455 °F	ASTM D648

### Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China