

Chase Plastics CP Pryme® NN113L (Dry) Nylon 66, 13% Glass Fiber Reinforced, Lubricated

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 10% Glass Fiber Filled

Material Notes:

Features: Good chemical resistanceGrease resistantLubricatedOil resistantHigh rigiditySolvent resistantHigh tensile strengthForm:
PelletsInformation provided by Chase Plastics.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chase-Plastics-CP-Pryme-NN113L-Dry-Nylon-66-13-Glass-Fiber-Reinforced-Lubricated.php

Physical Properties	Metric	English	Comments
Density	1.22 g/cc	0.0441 lb/in ³	ASTM D792
Filler Content	13 %	13 %	
Water Absorption	1.0 %	1.0 %	At 24 hrs; ASTM D570
Linear Mold Shrinkage, Flow	0.0040 - 0.0080 cm/cm	0.0040 - 0.0080 in/in	0.125 in; ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	95	95	ASTM D785
Tensile Strength at Break	124 MPa	18000 psi	ASTM D638
Elongation at Break	3.0 %	3.0 %	ASTM D638
Flexural Strength	179 MPa	26000 psi	ASTM D790
Flexural Modulus	5.52 GPa	800 ksi	ASTM D790
Izod Impact, Notched	0.801 J/cm	1.50 ft-lb/in	0.125 in; ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	260 °C	500 °F	
Deflection Temperature at 1.8 MPa (264 psi)	245 °C	473 °F	Unannealed; ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China