

## Chase Plastics CP Pryme® NN143GL (COND, 50% RH) Nylon 66, 43% Glass Fiber Reinforced, Internally Lubricated

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66 , 40% Glass Fiber Filled

**Material Notes:**

Information provided by Chase Plastics.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Chase-Plastics-CP-Pryme-NN143GL-COND-50-RH-Nylon-66-43-Glass-Fiber-Reinforced-Internally-Lubricated.php](http://www.lookpolymers.com/polymer_Chase-Plastics-CP-Pryme-NN143GL-COND-50-RH-Nylon-66-43-Glass-Fiber-Reinforced-Internally-Lubricated.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.50 g/cc	1.50 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	145 MPa	21100 psi	ASTM D638
Flexural Strength	225 MPa	32700 psi	ASTM D790
Flexural Modulus	7.58 GPa	1100 ksi	ASTM D790
Izod Impact, Notched	2.40 J/cm	4.50 ft-lb/in	ASTM D256

### Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China