

Chase Plastics CP Pryme® PC320GR Polycarbonate (Utility Grade), 20% Glass Fiber Reinforced, Mold Release

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, 20% Glass Filled

Material Notes:

Information provided by Chase Plastics.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chase-Plastics-CP-Pryme-PC320GR-Polycarbonate-Utility-Grade-20-Glass-Fiber-Reinforced-Mold-Release.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.34 g/cc	1.34 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	96.5 MPa	14000 psi	ASTM D638
Elongation at Break	3.0 %	3.0 %	ASTM D638
Flexural Strength	131 MPa	19000 psi	ASTM D790
Flexural Modulus	5.17 GPa	750 ksi	ASTM D790
Izod Impact, Notched	1.33 J/cm	2.50 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	135 °C	275 °F	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China