

Chem Polymer Chemlon 109-33 G Nylon 66, 33% Glass Fiber Reinforced

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 30% Glass Fiber Filled

Material Notes:

A highly toughened 33% glass fiber reinforced nylon 66 developed for applications requiring stiffness, creep resistance and impact resistance. Data provided by the manufacturer, Chem Polymer.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chem-Polymer-Chemlon-109-33-G-Nylon-66-33-Glass-Fiber-Reinforced.php

Physical Properties	Metric	English	Comments
Density	1.34 g/cc	0.0484 lb/in ³	ASTM D792

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	138 MPa	20000 psi	ASTM D638
Elongation at Break	3.0 %	3.0 %	ASTM D638
Flexural Yield Strength	203 MPa	29400 psi	ASTM D790
Flexural Modulus	6.90 GPa	1000 ksi	ASTM D790
Izod Impact, Notched	1.60 J/cm	3.00 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	254 °C	489 °F	ASTM D789
Deflection Temperature at 1.8 MPa (264 psi)	246 °C	475 °F	ASTM D648

Processing Properties	Metric	English	Comments
Melt Temperature	279 °C	534 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China