

Cheng Yu Plastic A702G15 ABS 15% Glass Fiber Reinforced

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), 20% Glass Fiber Filled

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Cheng-Yu-Plastic-A702G15-ABS-15-Glass-Fiber-Reinforced.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.15 g/cc	1.15 g/cc	ASTM D792
Linear Mold Shrinkage	0.0010 - 0.0040 cm/cm	0.0010 - 0.0040 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	102	102	ASTM D785
Tensile Strength, Yield	66.9 MPa	9700 psi	ASTM D638
Flexural Yield Strength	118 MPa	17100 psi	ASTM D790
Izod Impact, Notched	1.35 J/cm	2.53 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	107 °C	225 °F	ASTM D648
Flammability, UL94	HB	HB	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China